

providing first and second substrates;

forming first and second orientation films on the first and second substrates, respectively;

depositing a liquid crystal material on the first orientation film of the substrate, wherein the deposited liquid crystal material has a viscosity greater than about 20 to 50 mm^2/sec ;

forming a seal material at edges of the first substrate; and

attaching the first and second substrates.

RECEIVED
OCT 17 2002
TECHNOLOGY CENTER 2800

20 (AMENDED). A fabricating method for a liquid crystal display panel comprising:

providing first and second substrates;

forming first and second orientation films on the first and second substrates, respectively;

rubbing each of the first and second orientation films;

depositing a liquid crystal material on the first orientation film of the substrate, the liquid crystal material having a viscosity greater than 100 mm²/sec;

forming a seal material at edges of the first substrate;

attaching the first and second substrates; and

heat-treating the liquid crystal material to activate the liquid crystal and have substantially the same characteristics as a liquid crystal material having a viscosity of 20 to 50 mm²/sec.